

CHANG CHUN PETROCHEMICAL CO., LTD.

No.301, Songkiang Road, 7th Fl.,

Taipei 10477 TAIWAN

website: www.ccp.com.tw

Tel : 886-2-2500-1800

AE-6040V

TYPICAL PROPERTIES

Main Ingredient	VA-VEOVA
Appearance	Milky White
Protective Colloid	Polyvinyl Alcohol
Solids Content *(%)	54 ±2
Viscosity*(cP,25 °C,20rpm)	1000 - 4000
pH*	4.0 – 6.0
Free Monomer* (%)	0.2 max.
Tg (oC)	15±3
Particle Size (nm)	1000 – 2500

*marked item, are the ex-works delivery specification.

All other figures are typical physical properties for reference only.

INTRODUCTION //

A-6040V is a vinyl acetate vinyl versatate emulsion copolymer. Because of its very good adhesive properties, A-6040V is a raw material which is particularly suitable for the manufacture of adhesives for difficult to adhere substrates such as plastic films in the packaging, foams and paper applications. It is also suitable for floor, wall and ceiling adhesives. After drying it forms a clear, soft, flexible film with low surface tackiness, exhibits very good adhesive properties on an extremely wide range of plastic materials, and especially polyvinyl chloride (PVC) product. It's highly recommended for modification of systems containing cement and gypsum for floors, walls and ceilings. In combination with appropriate raw materials it can produce flexible, water resistant compounds that are highly resistant to saponification, aging, and light exposure. In the general formulations it can be combined with plasticizers, solvents, thickening agents, extenders etc. During processing in the recommended applications the product demonstrates excellent rheology and workability with reduced water demand and extended pot life, improved water retention capability, rapid wetting and high shear stability.

RECOMMENDED APPLICATIONS //

This multi purpose latex copolymer can be used in a wide range of applications, and is especially recommended for the wall-covering and construction adhesives, general purpose adhesives, wood putties, tile adhesive mortars, gypsum-based compounds (joint compounds, skim coatings, and textures), self-leveling floor compounds and decorative overlayers, interior gloss or semi-gloss masonry paints. In the cured state of appropriate applications the product improves adhesive bond strength on a wide variety of different substrates, freeze-thaw cycling resistance, flexibility, tensile strength and abrasion resistance.

SAFETY & STORAGE //

In general, A-6040V is considered safe for its intended use. However, since these product contains residual vinyl acetate monomer (less than 0.5%), it is recommended to have adequate ventilation where latex is handled. The usual protective measures apply when handling polymer emulsion such as wearing gloves and goggles. Splashes on the skin or in the eyes should be removed by irrigation with clean water.

The A-6040V should be stored between 5 and 40°C. Drums of the product should be stored in dry, sheltered area to be used within 6 months. Do not store latex under freezing condition. When containers are open they should be used as soon as possible or be resealed to prevent drying up.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of products is guaranteed under our General Conditions of Sale. Neither CCP nor its agents nor its distributors accept liability for damages arising from the use of our product or our recommendation. It is our customers' responsibility to avoid infringement of the rights of third parties.