

壓克力乳膠 ACRYLIC EMULSION

1.紡織業用乳膠 Acrylic Emulsion for textile industry

(1) 非織物、織物加工用乳膠 For non-woven fabric binder & fabric stiffening finish

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	Tg(°C)	特性 Features	用途 Uses
B-730	40.0±1.0	< 100	8.0~9.0	40	速乾、硬挺、耐水性 Fast drying、Stiffness、Water resistance	不織布、織物硬挺加工 Non-woven、Fabric stiffening finish
B-730C	40.0±1.0	<100	8.0~9.0	30	速乾、硬挺、耐水性 Fast drying、Stiffness、Water resistance	不織布、織物硬挺加工 Non-woven、Fabric stiffening finish
B-730D	40.0±1.0	<100	4.0~5.0	30	速乾、硬挺、耐水性 Fast drying、Stiffness、Water resistance	不織布、織物硬挺加工 Non-woven、Fabric stiffening finish
B-7335	35.0±1.0	<100	6.0~7.0	40	速乾、硬挺、耐水性 Fast drying、Stiffness、Water resistance	不織布、織物硬挺加工 Non-woven、Fabric stiffening finish

B-15E	35.0±1.0	1800~2800	6.0~7.0	30	速乾、硬挺、耐水性 Fast drying、Stiffness、Water resistance	不織布、織物硬挺加工 Non-woven、Fabric stiffening finish
PS-707	44.0±1.5	<100	8.5~9.5	80	速乾、硬挺、耐水性 Fast drying、Stiffness、Water resistance	不織布、織物硬挺加工 Non-woven、Fabric stiffening finish

(2) 絨毯背膠 Back-size binder for fabrics、rugs upholsteries

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	Tg(°C)	特性 Features	用途 Uses
B-1250A	40.0±1.0	3000~4000	5.0~8.0	-30	柔軟、耐洗、密著 Softness、Wash durable、Good adhesion	絨毯背膠、手感改質、補強 Back-sizing binder、Hand feeling modifier、Reinforce for fabric
B-1250F	40.0±1.0	<1000	3.0~5.0	-35	柔軟、耐洗、密著 Softness、Wash durable、Good adhesion	絨毯背膠、手感改質、補強 Back-sizing binder、Hand feeling modifier、Reinforce for fabric
B-1250M	40.0±1.0	500~1500	4.0~6.0	-30	柔軟、耐洗、密著 Softness、Wash durable、Good adhesion	絨毯背膠、手感改質、補強 Back-sizing binder、Hand feeling modifier、Reinforce for fabric

(3) 貼合用乳膠 For lamination adhesive

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	Tg(°C)	特性 Features	用途 Uses
B-145	45.0±1.5	5500~6500	5.0~7.0	0	耐水、密著、作業性 Water resistance、Good adhesion、Workability	布與 PVC 泡棉貼合 PVC foam sheet-fabrics lamination
B-145S	45.0±1.5	5500~6500	5.0~7.0	-7	耐水、密著、作業性 Water resistance、Good adhesion、Workability	布與 PVC 泡棉貼合 PVC foam sheet-fabrics lamination
B-1452	47.0±1.5	4000~6000	7.0~9.0	-3	耐水、密著、作業性 Water resistance、Good adhesion、Workability	布與 PVC 泡棉貼合 PVC foam sheet-fabrics lamination
B-145A	45.0±1.5	5500~6500	5.0~7.0	0	耐水、密著、耐黃變 Water resistance、Good adhesion、Yellowing resistance	布與 PVC 泡棉貼合 PVC foam sheet-fabrics lamination

(4) 植毛及印花加工用乳膠 For flocking adhesive & pigment printing binders

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	Tg(°C)	特性 Features	用途 Uses
-------------	-------------------------	----------------------------	----	--------	----------------	------------

B-3638	36.0±1.0	200~800	4.0~6.0	-40	柔軟、密著性、耐磨 Softness, Binding strength, Scrub resistance	顏料印花用膠料、紡織布植毛 Binder for pigment printing, Flocking for fabric
B-3640	40.0±1.0	200~800	5.0~7.0	-44	柔軟、密著性 Softness, Binding strength	顏料印花用膠料 Binder for pigment printing
B-3641	37.0±1.0	200~800	5.0~7.0	-42	柔軟、密著性 Softness, Binding strength	顏料印花用膠料 Binder for pigment printing
B-3611	45.0±1.5	200~800	4.0~5.0	-35	密著、耐洗、耐磨、顏料固著性 Adhesive, Wash & Scrub resistance, Pigment binding strength	顏料印花用膠料、紡織布植毛 Binder for pigment printing, Flocking for fabric
B-60	30.0±1.0	<100	2.5~3.5	23	高增黏性、耐水性 High thickening, Water resistance	增稠劑 Thickening agent

(5) 窗簾布塗佈用乳膠 Resin for curtain-fabric coating binders

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	Tg(°C)	特性 Features	用途 Uses
B-3643A	40.0±1.0	< 200	3.0~5.0	12	中軟、密著、顏料固著性 Middle softness, Good adhesion, Pigment binding strength	窗簾布塗佈、黏合劑 Coating binders for curtain-fabric

B-3643B	40.0±1.0	<200	3.0~5.0	6	中軟、密著、顏料固著性 Middle softness、Good adhesion、Pigment binding strength	窗簾布塗佈、黏合劑 Coating binders for curtain-fabric
B-3643C	40.0±1.0	<200	4.0~6.0	0	中軟、密著、顏料固著性 Middle softness、Good adhesion、Pigment binding strength	窗簾布塗佈、黏合劑 Coating binders for curtain-fabric
B-3643M	40.0±1.0	<200	3.0~5.0	5	中軟、密著、顏料固著性 Middle softness、Good adhesion、Pigment binding strength	窗簾布塗佈、黏合劑 Coating binders for curtain-fabric
B-3640H	43.0±1.5	200~800	5.0~7.0	-40	柔軟、密著性、顏料固著性 Softness、Good adhesion、 Pigment binding strength	窗簾布塗佈、黏合劑 Coating binders for curtain-fabric

2. 土木建築用乳膠 Acrylic emulsion for concrete architecture

(1) 壓克力改質水泥砂漿 For acrylic latex modified cement mortars

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	Tg(°C)	特性 Features	用途 Uses
PCM-810	40.0±1.0	500~2500	6.0~8.0	-8	耐水、密著、作業性、強度 Water resistance、Good	水泥增強、聚合物水泥、磁磚貼合 Reinforce cement、Polymer

					adhesion、Workability、Strength	modified cement、Tile grouts or mortars adhesive
PCM-8200	45.0±1.5	<500	7.0~9.0	0	耐水、耐鹼、作業性、強度 Water & Alkali resistance、 Workability、Strength	水泥增強、聚合物水泥、地坪 Reinforce cement、Polymer modified cement、Floor overlays
P-208H	46.0±1.5	500~1500	8.0~9.0	12	耐水、耐鹼、作業性、強度 Water & Alkali resistance、 Workability、Strength	水泥增強、聚合物水泥、地坪 Reinforce cement、Polymer modified cement、Floor overlays
PCM-1468	47.0±1.5	<300	8.0~10.0	-12	耐水、密著、耐候性、強度、無臭 Water resistance、Good adhesion、Durability、Strength	水泥增強、磁磚貼合、水泥修補 Reinforce cement、Tile adhesive、Repair mortars

(2) 彈性水泥砂漿用乳膠 Resin for elastic cement mortars

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	Tg(°C)	特性 Features	用途 Uses
P-8270	52.0±1.5	<300	7.0~8.0	-30	彈性、耐水、密著性 Elastic、Water resistance、Good adhesion	防水、水泥砂漿接著、耐龜裂 Waterproof、Mortar adhesive、 Crack resistance
P-8270B	52.0±1.5	500~1500	5.0~7.0	-25	彈性、耐水、密著性 Elastic、Water resistance、Good adhesion	防水、水泥砂漿接著、耐龜裂 Waterproof、Mortar adhesive、 Crack resistance

PCM-1433	46.0±1.5	<200	7.5~9.5	-20	彈性、耐水、密著性 Elastic、Water resistance、Good adhesion	防水、水泥砂漿接著、耐龜裂 Waterproof、Mortar adhesive、Crack resistance
PCM-8145	45.0±1.5	500~2000	6.5~7.5	-50	彈性、耐水、密著性 Elastic、Water resistance、Good adhesion	防水、水泥砂漿接著、耐龜裂 Waterproof、Mortar adhesive、Crack resistance

(3) 填縫、塗飾材料用乳膠 Resin for caulk & sealant、Decorative coating

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	Tg(°C)	特性 Features	用途 Uses
S-6180	55.0±1.5	500~3000	6.0~8.0	-5	密著性、彈性、顏料分散性 Good adhesion、Elastic、Pigment dispersion	填縫材料、塗飾材料 Caulk & Sealant、Decorative coating
S-6250	50.0±1.5	<300	7.0~9.0	-10	密著性、彈性、顏料分散性 Good adhesion、Elastic、Pigment dispersion	填縫材料、塗飾材料 Caulk & Sealant、Decorative coating

3. 塗料用壓克力乳膠 Acrylic emulsion for paint

品名 Grade	固形份(%) Solid content	黏度 Viscosity cps / 25°C	PH	MFT(°C)	特性 Features	用途 Uses
-------------	-------------------------	----------------------------	----	---------	----------------	------------

P-108	46.0±1.5	500~1500	8.0~9.0	17	光澤、密著、耐水、耐污染 Gloss、Adhesive、Water & Stain resistance	室內外光澤、半光澤水性塗料 Interior、 exterior gloss or semi-gloss masonry paints
P-208	46.0±1.5	500~1500	8.0~9.0	17	光澤、密著、耐水、耐污染、作業性 Gloss、Adhesive、Water & Stain resistance、Workability	室內外光澤、半光澤水性塗料 Interior、 exterior gloss or semi-gloss masonry paints
P-608	46.0±1.5	500~1500	8.0~9.0	17	耐候，耐水、耐鹼，顏料分散性 Weather resistance、Water & Alkali resistance、Pigment dispersion	室內外光澤、半光澤水性塗料 Interior or exterior gloss or semi-gloss masonry paints
P-142	46.0±1.5	500~1500	8.0~9.0	16	密著、耐鹼、耐水、耐污染 Good adhesion、Alkali、Water & Stain resistance	平光水泥漆、複層模樣塗料 Flat masonry paints、multilayer mastic paints
P-143	46.0±1.5	50~300	7.5~8.5	6	柔性、密著性、耐水、耐鹼 Softness、Good adhesion、Water & Alkali resistance	水泥漿接著、封鹼粉刷、塗料底漆 Mortars adhesive、Alkali sealer、Primer for multilayer mastic paints
P-3450	45.0±1.5	500~2000	6.5~7.5	<0	彈性、低溫造膜、耐久性 Elastic、Low M.F.T.、Weather durable	彈性複層模樣塗料 Elastic multilayer mastic paints
P-3460	54.0±1.5	<1500	8.5~9.5	<0	彈性、低溫造膜、耐久性	彈性複層模樣塗料
P-1280	50.0±1.5	<1000	7.0~9.0	10	光澤、密著、耐水、耐污染、作業性 Gloss、Adhesive、Water & Stain resistance、Workability	顏料、填料塗佈黏合劑，光澤、半光澤水性塗料 Binder for pigmented & filled coatings、Gloss or semi-gloss masonry paints

P-1280H	54.0±1.5	<500	7.0~9.0	5	高固型份、密著、耐水、作業性、 顏料分散性 High solid、Adhesive、Water resistance、Workability、Pigment dispersion	顏料、填料塗佈黏合劑，光澤、半 光澤水性塗料 Binder for pigmented & filled coatings、Gloss or semi-gloss masonry paints
---------	----------	------	---------	---	---	---