

長春人造樹脂廠股份有限公司
CHANG CHUN PLASTICS CO., LTD.

台北市松江路301號7樓

FAX:(02)25018317 No.301 SONGKIANG ROAD,7FL.,TAIPEI. TAIWAN TEL:(02)25001800(REP)

Technical Data Sheet

BISPHENOL A (BPA)

| Items | Spec. |
|---------------------------------------|--------------|
| 1.Purity(dry basis),wt% | ≥ 99.80 |
| 2. Phenol,wt-ppm | ≤ 100 |
| 3. Water,wt% | ≤ 0.100 |
| 4. Freezing Point, $^{\circ}\text{C}$ | ≥ 156.5 |
| 5. Methanol Color,APHA | ≤ 20.0 |
| 6. Iron,wt-ppm | ≤ 1.00 |
| 7. Ash,wt-ppm | < 20 |
| 8. Molten Color,APHA | ≤ 30 |