

Technical Specification

Spec.	Diam. Range (mm)	Times	Density (g/L)	Blowing Agent (%)	Residual SM (ppm)	Moisture (%)	Coating Agent (ppm)	Oxygen Index (%)
P-201	1.60-2.00	90-105	8-11	6.5-7.5	≤5000	≤1%	≤3200	N.A.
P-301	1.00-1.60	75-90	11-13					
P-302	0.85-1.25	65-75	13-15					
P-303	0.70-0.90	55-70	14-18					
P-401	0.50-0.80	45-55	18-20					
P-501	0.40-0.60	40-50	20-25					
F-201	1.60-2.50	85-100	8-12	6.2-7.3	≤2000	≤2%	≤3200	≥30
F-301	1.00-1.60	70-85	12-14					
F-302	0.85-1.25	60-70	14-16					
F-303	0.70-0.90	50-65	15-18					
F-401	0.50-0.80	40-50	18-25					
F-501	0.40-0.60	30-45	25-30					
HFC-301	1.00-1.60	55-70	14-18	5.5-6.8	≤2000	≤2%	≤3200	≥30
HFC-302	0.85-1.25	50-60	16-20					
HFC-303	0.70-0.90	40-55	18-25					
HFC-401	0.50-0.80	35-45	22-30					
HFC-501	0.40-0.60	30-40	25-35					

