

長春石油化學股份有限公司

臺北市松江路三〇一號七樓

CHANG CHUN PETROCHEMICAL CO., LTD.

NO.301 SONGKIANG ROAD, 7TH FL.,

TAIPEI, 10477 TAIWAN

TEL: 886-2-25187928

FAX: 886-2-25033378

THE SPECIFICATION OF POLYVINYL ACETATE

Grade	Solid Content > %	Ph Value	Viscosity cps	Type/Rotational Speed/Temperature
AE600	60.0±1.5	4~6	50,000 - 80,000	LVT/6rpm/30°C
AE6020	55.0±1.0	4~6	3,000 - 5,000	LVT/ 60rpm/30°C
AE6020R	55.0±1.5	4~6	3,000 - 5,000	RVT/20rpm/30°C
AE6020M	55.0±1.5	4~6	3,000 - 5,000	LVT/60 rpm/30°C
AE6020V	55.0±1.5	4~6	3,000 - 5,000	LVT/60rpm/30°C
AE6036	56.5±1.5	4~6	2,700 - 3,500	RVT/20rpm/25°C
AE6016	55.0±1.5	4~6	approx.2,000	RVT/20rpm/30°C
AE6030S	50.0±1.5	4~6	approx.5,000	LVT/60rpm/30°C
AE6050	50.0±1.5	4~6	approx.5,000	RVT/20rpm/30°C
AE6050S	50.0±1.5	4~6	approx.5,000	RVT/20rpm/30°C
AE4010	40.0±1.5	4~6	approx.1,000	RVT/20rpm/30°C
AE5010	50.0±1.5	4~6	approx.1,000	RVT/20rpm/30°C
AE7010H	60.0±1.5	4~6	approx.1,000	RVT/20rpm/30°C
TM5016	50.0±1.5	4~6	approx.800	RVT/20rpm/30°C
PE5010	50.0±1.5	4~6	approx.800	RVT/20rpm/30°C